

# IMPERSEP® 200

## Product description



0099

NP EN 13249 / 13250 / 13251 / 13252 / 13253

NP EN 13254 / 13255 / 13256 / 13257 / 13265

### Constitucion

#### Material:

Non woven synthetic fiber with 200 g/m<sup>2</sup> (+10%; -15%) of a weight.

#### Presentation:

250, 0 m<sup>2</sup> rolls (2, 0 m x 125, 0 m).

### Technical characteristics:

Characteristics	Values	Unit	Tests
Resistência à tração longitudinal	2,0 (-0,3)	kN/m	EN 13249:2000/A1:2005 EN 13250:2000/A1:2005 EN 13251:2000/A1:2005 EN 13252:2000/A1:2005/ERRATUM:2001 EN 13253:2000/A1:2005 EN13254:2000/AC:2003/A1:2005 EN 13255:2000/AC:2003/A1:2005 EN 13256:2000/A1:2005 EN 13257:2000/A1:2005 EN 13265:2000/AC:2003/A1:2005 -
Resistência à tração transversal	2,0 (-0,3)	kN/m	
Alongamento longitudinal	90 ± 30	%	
Alongamento transversal	80 ± 30	%	
Resistance to static perforation (CBR)	0,4 (-0,2)	kN	
Resistance to dynamic perforation (cone)	27 (+3)	kN	
Opening extent	90 ± 20	µm	
Water permeability	0,03731 (-0,005)	m/s	
Water flow in the plane	20 kPa: 1,57*10 <sup>-6</sup> (-0,1+10 <sup>-7</sup> )	m <sup>2</sup> /s	
Protection effectiveness	12,0*10 <sup>3</sup> (-0,3*10 <sup>3</sup> )	kN/m <sup>2</sup>	
Durability	>25; natural soil; 4<pH<9; T<25°C	Anos	

#### Notes:

- Rot proof material, insensitive to microbial agents attack.
- Great durability, resistance to acids, bases and U.V.
- Technical data specified above were calculated based on regular testing.
- The values are indicative and obtained from current production.

#### Intended uses:

- Separator.

#### Handling and storage recommendations:

- Prevent falls and bumps.
- Transport and store rolls protected from the weather – sun, rain, frost, hail and snow.

Impersep is a registered trademark of Imperialum.

#### HEAD OFFICE AND PLANT

Zona Industrial - Pau Queimado  
2870 - 100 Montijo

Tel.: 212 327 100  
Fax: 212 327 101

#### NORTH AREA TRADE DELEGATION

Rua da Venda Nova, 24  
4415 - 366 Pedroso

Tel. 229 961 664 | 227 860 860  
Fax: 227 848 267

#### CENTER AREA TRADE DELEGATION

Armazéns Vales Pedrulha - Arm. 11, Piso 0  
Zona Industrial da Pedrulha  
3020 - 320 Coimbra

Tel. 239 492 356  
Fax: 239 492 827

#### IMPERLIS TRADE DELEGATION

Rua Estevão de Amarante, 4 - Ramada  
2675-785 Odivelas

Tel. 219 334 986  
Fax: 219 310 183

#### SOUTH AREA TRADE DELEGATION

EN 125 - Parque Industrial Bela Mandil -  
Armazém 1  
8700 - 172 Oihão

Tel. 289 703 396  
Fax: 289 707 936